

Test Report

No. NGBEC1900836101

Date: 19 Mar 2019

Page 1 of 5

NINGBO LARGE STONES HARDWARE&ELECTRICAL TRADING CO.,LTD.
NO.D-58,TIANDESHANGDU,YUYAO,NINGBO,ZHEJIANG


The following sample(s) was/were submitted and identified on behalf of the clients as : Stainless steel fasteners

SGS Job No. : NP19-000724 - NB
 Date of Sample Received : 11 Mar 2019
 Testing Period : 11 Mar 2019 - 19 Mar 2019
 Test Requested : Selected test(s) as requested by client.
 Test Method : Please refer to next page(s).
 Test Results : Please refer to next page(s).

Result Summary :

Test Requested	Conclusion
Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004 –Sensorial examination odour and taste test (sample 001)	PASS
Council of Europe Resolution CM/Res(2013)9–Extractable heavy metal (sample 001)	PASS

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Ningbo Branch



Iris Xiao
Approved Signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Ningbo Branch Chemical Laboratory

15/F West of Building 4, Lingyun Industry Park, No.1177 Lingyun Road, Ningbo National Hi-Tech Zone, Ningbo, Zhejiang, China 315040 t E&E (86-574)89070249 www.sgs.com.cn
 中国·浙江·宁波市国家高新区凌云路1177号凌云产业园4号楼西1-5层 邮编: 315040 t HL (86-574)89070271 t ML (86-574)89070242 e sgs.china@sgs.com

Test Report

No. NGBEC1900836101

Date: 19 Mar 2019

Page 2 of 5

Test Results :

Test Part Description :

Specimen No.	SGS Sample ID	Description	Material (claimed by the client)
SN1	NGB19-008361.001	Silvery metal screw	Stainless steel

Remarks :

- (1) mg/dm² = milligram per square decimeter
- (2) mg/kg = milligram per kilogram
- (3) °C= degree Celsius
- (4) < = less than
- (5) MDL = Method Detection Limit
- (6) ND = Not Detected (< MDL)

Regulation (EC) No 1935/2004 of the European Parliament and of the Council of 27 October 2004 –Sensorial examination odour and taste test (sample 001)

Test Method : With reference to DIN 10955:2004
 Test media: Distilled water
 No. of panelist: 6

Test Item(s)	Limit	001
Test time(hr)	-	24
Temperature(°C)	-	70
Sensorial examination odour (Point scale)	2.5	0
Sensorial examination taste (Point scale)	2.5	0

Notes :

- Scale evaluation:
- 0 – no perceptible difference
 - 1 – just perceptible difference
 - 2 – slight difference
 - 3 – marked difference
 - 4 – strong difference

Council of Europe Resolution CM/Res(2013)9–Extractable heavy metal (sample 001)

Test Method : With reference to EN 13130-1:2004, analysis was performed by ICP-MS.

Sample 001:



Test Report

No. NGBEC1900836101

Date: 19 Mar 2019

Page 3 of 5

Simulant Used : Artificial tap water

Test Condition : 70 °C 24.0 hr(s)

<u>Test Item(s)</u>	<u>Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>1st + 2nd Migration</u>
Aluminium (Al)	35	mg/kg	0.2	ND
Antimony (Sb)	0.28	mg/kg	0.02	ND
Chromium(Cr)	1.75	mg/kg	0.1	ND
Cobalt(Co)	0.14	mg/kg	0.01	ND
Copper(Cu)	28	mg/kg	0.1	0.2
Iron(Fe)	280	mg/kg	0.25	1.89
Manganese(Mn)	12.6	mg/kg	0.25	0.52
Molybdenum(Mo)	0.84	mg/kg	0.02	ND
Nickel(Ni)	0.98	mg/kg	0.05	ND
Silver(Ag)	0.56	mg/kg	0.03	ND
Tin(Sn)	700	mg/kg	5	ND
Vanadium(V)	0.07	mg/kg	0.005	ND
Zinc(Zn)	35	mg/kg	1	ND
Arsenic(As)	0.014	mg/kg	0.001	ND
Barium(Ba)	8.4	mg/kg	0.25	ND
Beryllium(Be)	0.07	mg/kg	0.005	ND
Cadmium(Cd)	0.035	mg/kg	0.002	ND
Lead(Pb)	0.07	mg/kg	0.005	ND
Lithium(Li)	0.336	mg/kg	0.02	ND
Mercury(Hg)	0.021	mg/kg	0.002	ND
Thallium(Tl)	0.0007	mg/kg	0.0001	ND

<u>Test Item(s)</u>	<u>Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>3rd Migration</u>
Aluminium (Al)	5	mg/kg	0.2	ND
Antimony (Sb)	0.04	mg/kg	0.02	ND
Chromium(Cr)	0.25	mg/kg	0.1	ND
Cobalt(Co)	0.02	mg/kg	0.01	ND
Copper(Cu)	4	mg/kg	0.1	ND
Iron(Fe)	40	mg/kg	0.25	ND
Manganese(Mn)	1.8	mg/kg	0.25	ND
Molybdenum(Mo)	0.12	mg/kg	0.02	ND
Nickel(Ni)	0.14	mg/kg	0.05	ND
Silver(Ag)	0.08	mg/kg	0.03	ND
Tin(Sn)	100	mg/kg	5	ND
Vanadium(V)	0.01	mg/kg	0.005	ND
Zinc(Zn)	5	mg/kg	1	ND
Arsenic(As)	0.002	mg/kg	0.001	ND
Barium(Ba)	1.2	mg/kg	0.25	ND
Beryllium(Be)	0.01	mg/kg	0.005	ND



SGS-CSTC Technical Services Co., Ltd.
Ningbo Branch Chemical Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

15/F West of Building 4, Lingyun Industry Park, No.1177 Lingyun Road, Ningbo National Hi-Tech Zone, Ningbo, Zhejiang, China 315040 t E&E (86-574)89070249
中国·浙江·宁波市国家高新区凌云路1177号凌云产业园4号楼西1-5层 邮编: 315040 t HL (86-574)89070271 t ML (86-574)89070242 e sgs.china@sgs.com

www.sgs.com

Test Report

No. NGBEC1900836101

Date: 19 Mar 2019

Page 4 of 5

<u>Test Item(s)</u>	<u>Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>3rd Migration</u>
Cadmium(Cd)	0.005	mg/kg	0.002	ND
Lead(Pb)	0.01	mg/kg	0.005	ND
Lithium(Li)	0.048	mg/kg	0.02	ND
Mercury(Hg)	0.003	mg/kg	0.002	ND
Thallium(Tl)	0.0001	mg/kg	0.0001	ND

Notes :

- (1) Test condition & simulant were specified by client.
- (2) Requirement for repeat use article: According to Council of Europe Resolution CM/Res(2013)9, the result from 3rd migration shall comply with the Specific Release Limit (SRL) and the sum of 1st and 2nd migration shall not exceed seven times of SRL for repeated use articles
- (3) The ratio of surface area to volume ratio was 6.0 dm² per 1 kg of foodstuff in contact with.
- (4) Acidic foodstuff is not considered for compliance



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

Sample photo:



SGS authenticate the photo on original report only

*** End of Report ***

